

## Description

**CASABOND TXE** provides a useful means of bonding rubber doughs, solution coatings and solvent based dips to a variety of synthetic textiles.

## Typical Properties

Appearance	low viscosity liquid
Colour	dark brown
Density @ 20°C (Kg/m <sup>3</sup> )	1020
Active Material Content (%)	54
Solvent	ethyl acetate

## Applications

**CASABOND TXE** is added to the rubber or solution prior to use (up to 8 hours max), and the bond is formed during normal vulcanisation. Once the **CASABOND TXE** is added the solution has limited potlife. **CASABOND TXE** is a useful additive for footwear adhesives particularly for those based on polychloroprene and on chlorinated rubbers.

## Packaging

**CASABOND TXE** is packed in 50 kg net weight metal drums.

## Shelf Life

**CASABOND TXE** should be stored under cool and dry conditions in a well ventilated area. Direct exposure to sunlight should be avoided. It is recommended that the material be used within 12 months of certification

## Handling

Consult relevant Material Safety Data Sheet.