

Description

CASABOND TX provides a useful means of bonding rubber doughs, solution coatings and solvent based dips to a variety of synthetic textiles.

Typical Properties

Appearance	low viscosity liquid
Colour	dark brown
Density at 20°C (Kg/m ³)	1070
Active Material Content (%)	54
Solvent	xylene

Application

CASABOND TX is added to the rubber dough or solution prior to use (up to 8 hours maximum), and the bond is formed during normal vulcanization. Once the **CASABOND TX** is added the solution has a limited pot life. **CASABOND TX** is a useful additive for footwear adhesives particularly for those based on polychloroprene and on chlorinated rubbers.

Packaging

CASABOND TX is packed in 50 kg nett weight metal drums.

Shelf Life

CASABOND TX should be stored under cool and dry conditions in a well ventilated area. Direct exposure to sunlight should be avoided. It is recommended that the material be used within 12 months of certification.

Handling

Consult relevant Material Safety Data Sheet.